Chemical Resistance of ENSINGER Engineering Plastics

CHEMICAL AGENTS

Trade Name	Raw Material Group	Acetamide 50%	Acetic Acid conc.	Acetic Acid 10%	Acetic Acid 5%	Acetone	Ammonia 10%	Benzene	Bitumen	Boric Acid 10%	Butylacetate	Butylene Glycol	Calcium Chloride 10%	Carbon Disulphide	Carbon Tetrachloride	Chlorobenzene	Chloroform	Citric Acid 10%	Clophen A 60 50%
TECAST™	Cast Nylon 6	+	–	–	(+)	+	+	+	(+)	–	+	+	–	+	+	+	–	(+)	+
TECAMID™ 6/6	Nylon 6/6	+	–	–	(+)	+	+	+	(+)	–	+	+	–	+	+	+	–	(+)	+
TECAPET™ PET	PET (Polyethylene Terephthalate)		(+)	+	+	+	–	+			+		+	+	+	–	–	+	+
TECAFORM™	Acetal Copolymer		–	(+)	+	+	(+)	(+)	+	+			+	+	+	+	+	+	
DELRIN®	Acetal Homopolymer		–	–	+	+	–	+	+	+			+	+	+	+	+	–	
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)		–	(+)	+	–	+	–				–			–	–	–		
NORYL®	PPO (Polyphenylene Oxide)		+	+	+	–	+	–							–		–	+	
TECANAT™	Polycarbonate		–	+	+	–	–	–	–	+	–	+	+	–	–	–	–	+	
TECASON™ S	Polysulfone		+	+	+	–	(+)	–			(+)		+		(+)		–	+	
TECAFINE™ PP	Polypropylene		+	+	+	+	+	(+)		+	(+)	+	+	(+)	–	+	(+)	+	
ULTEM®	Polyetherimide			+	+	+	–								+		–	+	
TECAPEEK™	Polyetheretherketone		+	+	+	+	+	+		+		+		+	+	+			
TECATRON™	PPS (Polyphenylene Sulfide)		+	+	+	+	+	+		+	+		+	+	+		+	+	
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)	+	+	+	+	–	+	+		+	+	+	+	+	+	+	+	+	

Trade Name	Raw Material Group	Copper Sulphate	Cyclohexane	Cyclohexanol	Cyclohexanone	Decahydronaphthalene	Diesel Oil	Dimethylformamide	Dioctylphthalate	Dioxane	Edible Oil, Edible Fat	Ethanol 96%	Ether	Ethyl Acetate	Ethylene Chloride	Formaldehyde 30%	Formamide	Formic Acid 10%	Frigen, Freon
TECAST™	Cast Nylon 6	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	–	+
TECAMID™ 6/6	Nylon 6/6	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	–	+
TECAPET™ PET	PET (Polyethylene Terephthalate)						+			+	+	+	+	+	–			+	+
TECAFORM™	Acetal Copolymer	+	+	+			+	+	+	+	+	+	+	–	+	+		–	
DELRIN®	Acetal Homopolymer	+	+	+			+	+	+	+	+	+	+	+	+	+		–	
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)		–	–	–		–		–		–	–		–	–				
NORYL®	PPO (Polyphenylene Oxide)	+	+	+		–	+		+	(+)	+	+		+		+		+	+
TECANAT™	Polycarbonate	+	–	(+)	–	+	(+)	–	(+)	–	+	(+)	–	–	–			+	–
TECASON™ S	Polysulfone		+				+		+			+	+	–					+
TECAFINE™ PP	Polypropylene		+	+	+		(+)	+	+	(+)		+		+	(+)	+	+	+	–
ULTEM®	Polyetherimide		+				+					+	+	(+)				+	+
TECAPEEK™	Polyetheretherketone		+				+	+			+	+		+				(+)	+
TECATRON™	PPS (Polyphenylene Sulfide)	+	+	+	+		+		+	+	+	+	+	+	+	+		+	+
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)	+	+	+	+		+	–		(+)	+	+	+	(+)	+	+		+	(+)

Trade Name	Raw Material Group	Fruit Juices	Fuel Oil	Gasoline	Glycerine	Glycol	Glysantin 40%	Heptane/Hexane	Hydrochloric Acid 36%	Hydrochloric Acid 2%	Hydrofluoric Acid	Hydrogen Peroxide 30%	Hydrogen Peroxide 0.5%	Hydrogen Sulphide	Ink	Isooctane	Isopropanol	Lactic Acid 90%	Lactic Acid 10%
TECAST™	Cast Nylon 6	+	+	+	+	+	+	+	–	–	–	–	–	–	+	+	+	–	(+)
TECAMID™ 6/6	Nylon 6/6	+	+	+	+	+	+	+	–	–	–	–	–	–	+	+	+	–	(+)
TECAPET™ PET	PET (Polyethylene Terephthalate)	+	+	+	+	+	+	+	–	+	(+)	+	+		+		(+)		
TECAFORM™	Acetal Copolymer	+	+	+	+	+	+	+	–	–	–	–	–	(+)		+	+	–	(+)
DELRIN®	Acetal Homopolymer	+	+	+	+	+	+	+	–	–	–	–	–	–		+	+	–	(+)
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)	(+)	–	–	+	–		+	+	+					–		–		
NORYL®	PPO (Polyphenylene Oxide)	+	+	+	+	+	+	+	+	+	+	+	+	+		+	+	+	+
TECANAT™	Polycarbonate	+	+	+ to –	(+)	+	+	+	+	+	(+)	+	+	+	+		(+)	+	+
TECASON™ S	Polysulfone			+	+	+	+	+	(+)	+	(+)	(+)	+			+	(+)		
TECAFINE™ PP	Polypropylene	+	(+)		+	+		+	+	+	+	+	+	+		+	+	+	+
ULTEM®	Polyetherimide	+	+	+		+		+	+	+							+		
TECAPEEK™	Polyetheretherketone	+	+	+	+	+		+	+	+	–	+	+	+	+	+	+	+	+
TECATRON™	PPS (Polyphenylene Sulfide)	+	+	+	+	+		+	+	+	+	–	+	+			+	+	+
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+

Trade Name	Raw Material Group	Linseed Oil	Methanol	Methyl Ethyl Ketone	Methylene Chloride	Milk	Motor Oil/Engine Oil	Nitric Acid 2%	Nitrobenzene	Oxalic Acid 10%	Ozone	Paraffin Oil	Perchlorethylene	Petroleum White Spirit	Phenol, Aqueous	Phosphoric Acid 10%	Potassium Hydroxide Solution 50%	Potassium Hydroxide Solution 10%	Potassium Dichromate 10%
TECAST™	Cast Nylon 6	+	+	+	(+)	+	+	–	(+)	(+)	–	+	+	+	–	–	(+)	+	(+)
TECAMID™ 6/6	Nylon 6/6	+	+	+	(+)	+	+	–	(+)	(+)	–	+	+	+	–	–	(+)	+	(+)
TECAPET™ PET	PET (Polyethylene Terephthalate)	+	+	+	–		+	+				+	(+)	+	(+)	+	–	(+)	+
TECAFORM™	Acetal Copolymer	+	+	+	(+)	+	+	–	+	(+)	(+)	+	+	+	–	–	+	+	+
DELRIN®	Acetal Homopolymer	+	+	+	+	+	+	–	(+)	(+)	–	+	+	+	–	–	–	–	(+)
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)		–	–	–	–		+					–	–	–				
NORYL®	PPO (Polyphenylene Oxide)	+	+	–		+	+	+		+		+		+		+	+	+	+
TECANAT™	Polycarbonate	+	–	–	–	+		+	–	+	+	+	(+)	–	–	+	–	–	+
TECASON™ S	Polysulfone		+	–	–		+	+		+			–			+			
TECAFINE™ PP	Polypropylene	+	+	+	(+)	+		(+)	+	+	(+)	+	(+)		+	+	+	+	
ULTEM®	Polyetherimide		+	(+)	–		+	+					+	+	(+)	+		+	
TECAPEEK™	Polyetheretherketone	+	+	+	+	+	+	+	+		+	+	+	+	+	+	+	+	+
TECATRON™	PPS (Polyphenylene Sulfide)	+	+	+	+	+	+	+	+	+		+	+	+	+	+	+	+	+
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)	+	+	–	+	+	+	+	+	+	+	+	+	+	+	+	–	(+)	+

Trade Name	Raw Material Group	Potassium Permanganate 1%	Propanol	Pyridene	P3-Solution, Aqueous	Salicylic Acid	Silicone Oil	Soap Solution	Soda Solution 10%	Sodium Bisulphite	Sodium Carbonate 10%	Sodium Chloride 10%	Sodium Hydroxide Solution 50%	Sodium Hydroxide Solution 5%	Sodium Nitrate 10%	Sodium Thiosulphate	Styrene	Sulphuric Acid 98%	Sulphuric Acid 2%
TECAST™	Cast Nylon 6	–	+	+	+	+	+	+	+	+	+	+	–	–	+	+	+	–	(+)
TECAMID™ 6/6	Nylon 6/6	–	+	+	+	+	+	+	+	+	+	+	–	–	+	+	+	–	(+)
TECAPET™ PET	PET (Polyethylene Terephthalate)	+	(+)				+	+	+	+	+	+	–	(+)	+	+		–	+
TECAFORM™	Acetal Copolymer	+	+	+			+	+		–	+	+	+	+	+	+		–	–
DELRIN®	Acetal Homopolymer	+	+	+			+	+		–	+	+	–	–	+	+		–	–
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)		–				–	+				+	+	+			–		+
NORYL®	PPO (Polyphenylene Oxide)	+	+				+	+			+	+	+	+			–	+	+
TECANAT™	Polycarbonate	+	+	–	–		+	+	+	+	+	+	–	–			–	–	+
TECASON™ S	Polysulfone							+				+		+				–	+
TECAFINE™ PP	Polypropylene	+	+	(+)			+	+	+	+	+	+	+	+	+	+		–	+
ULTEM®	Polyetherimide		+											+					+
TECAPEEK™	Polyetheretherketone		+				+	+	+		+	+	+	+			+	–	+
TECATRON™	PPS (Polyphenylene Sulfide)	+	+				+	+				+	+	+	+	+	+		(+)
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)	+	+	+		+	+	+	+	+	+	+	–	–	+	+		+	+

Trade Name	Raw Material Group	Tar	Tartaric Acid	Tetrahydrofuran	Tetrahydronaphthalene	Tincture of Iodine (alc.)	Toluene	Triethanolamine	Trichloroethylene	Trilon B 10%	Urea Aqueos	Vaseline	Water, Cold	Water, Hot	Wax, Molten	Wine, Brandy	Xylene	Zinc Chloride 10%
TECAST™	Cast Nylon 6	+	+	+	+	–	+	+	+	+	+	+	+	(+)	+	+	+	(+)
TECAMID™ 6/6	Nylon 6/6	+	+	+	+	–	+	+	+	+	+	+	+	(+)	+	+	+	(+)
TECAPET™ PET	PET (Polyethylene Terephthalate)			(+)	+		+		(+)			+	+	+	+		+	
TECAFORM™	Acetal Copolymer		(+)	+	+		+	+	+		+	+	+	+	+	+	+	+
DELRIN®	Acetal Homopolymer		(+)	+	+		+	(+)	+		+	+	+	+	+	+	+	
TECARAN™ ABS	ABS (Acrylonitrile-Butadiene-Styrene)						–					+	+		–		–	
NORYL®	PPO (Polyphenylene Oxide)		+			+			–		+		+	+	+	+	–	+
TECANAT™	Polycarbonate		+	–	–	(+)	–	–	–		+	+	+	(+)	+	+	–	+
TECASON™ S	Polysulfone						–		–				+	(+)			–	
TECAFINE™ PP	Polypropylene		+	–	–		(+)	+	(+)		+	+	+			+	–	+
ULTEM®	Polyetherimide						(+)		–				+	+			(+)	+
TECAPEEK™	Polyetheretherketone	+			(+)	+			+			+	+	+	+	+	+	+
TECATRON™	PPS (Polyphenylene Sulfide)	+	+	+	+		+	+	+		+	+	+	+		+	+	+
TECAFLON™ PVDF	PVDF (Polyvinylidene Fluoride)		+	(+)			+	+	+		+	+	+	+	+	+	+	+

™ Ensinger Industries, Inc.
Delrin® – Dupont Company
Ultem®, Noryl® – Sabic Innovative Plastics

The above results are the summary of several tests. The better resistance of the high-crystalline semi-finished products in comparison to injection molded thin parts which have been cooled rapidly and the smaller swelling of the EP-plastics are the result of Ensinger's special manufacturing process.

\+ = good
(+) = fair
– = poor

Test-Temperature 20°C

This information is only to assist and advise you on current technical knowledge and is given without obligation or liability. All trade and patent rights should be observed. All rights reserved.

SAN DIEGO PLASTICS, INC.
2220 McKINLEY AVENUE, NATIONAL CITY, CA 91950
619/477-4855 FAX 477-4874
www.sdplastics.com